



P.O. Box 120
Findlay, Ohio 45839-0120
Phone: 419-422-4341 Fax: 419-422-3952

Typical Analysis for #80 Dried Dolomite

Chemical

(Approximate Chemical Formula is $\text{CaCO}_3 \text{ MgCO}_3$)

Calcium Carbonate (CaCO_3)	54.5% CaO Equivalent = 30.5%
Magnesium Carbonate (MgCO_3)	44.3% MgO Equivalent = 21.2%
Silica (SiO_2)	0.8%
Iron Oxide (Fe_2O_3)	0.15%
Alumina (Al_2O_3)	0.15%
Sulphur (S)	0.15%
Loss on Ignition	47%

Physical

(U.S. Standard Sieve Series)

<u>Mesh</u>	<u>% Retained</u>	<u>% Passing</u>
20	Trace	99.9+
30	Trace	99.9+
70	0.7	99.5
100	1	98.5
140	4	94.5
200	9	85
325	25	60
Pan	60	

- Moisture content is less than 0.2%
- Average weight per cubic foot is 75 to 90 pounds
- Available in bulk (enclosed truck or rail car)
at our Carey, Ohio dolomite plant
- Available in 50 pound paper bags at our
Upper Sandusky, Ohio Packaging Plant

The analysis set forth above is generally typical of the product described.

NATIONAL LIME & STONE COMPANY MAKES NO WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR ANY PARTICULAR PURPOSE. THE DETERMINATION OF PRODUCT SUITABILITY FOR ANY PARTICULAR USE IS THE SOLE RESPONSIBILITY OF THE PURCHASER AND USER.

This Product is NOT intended to be used as a food source, component or ingredient. It is NOT produced in compliance with state or federal regulations governing products consumed or intended for consumption by humans or animals and should not be used for such purposes.

IN THE EVENT OF BREACH OF ANY WARRANTY OF ANY TYPE, THE SOLE REMEDY OF THE PURCHASER AND/OR USER SHALL BE REPLACEMENT OF THE PRODUCT PURCHASED. UNDER NO CIRCUMSTANCES WILL SELLER BE LIABLE FOR DAMAGES INCLUDING INCIDENTAL OR CONSEQUENTIAL DAMAGES, REGARDLESS OF THE LEGAL THEORY UPON WHICH A CLAIM MAY BE BASED.